

## **AZ 4562 – run sheet**

Merck (AZ Electronic Materials)

[nanyte.com/photoresists/az-4562](https://nanyte.com/photoresists/az-4562) · last updated 2026-07-26

**Thickness:** 5.1–8.8  $\mu\text{m}$

**Softbake:** 100 °C · 50 s · hotplate

**Develop:** Developer AZ 340 (AZ 400K also usable) · Dilution AZ 340 diluted 1:5 with water; no dilution stated for AZ 400K.

**Hardbake:** 115 °C · 50 s