

AZ ECI 3007 – run sheet

Merck

[nanyte.com/photorelists/az-eci-3007](https://www.merck.com/photorelists/az-eci-3007) · last updated 2026-07-26

Thickness: 0.6–1.1 μm

Softbake: 90–110 °C · 60 s

Post-exposure bake: 110 °C · 60 s–1.5 min

Develop: Time 60 s

Hardbake: 100–115 °C