

AZ ECI 3027 – run sheet

Merck (AZ Electronic Materials)

[nanyte.com/photorelists/az-eci-3027](https://www.merck.com/photorelists/az-eci-3027) · last updated 2026-07-26

Thickness: 2.4–4.4 μm

Softbake: 100 °C (90–110 °C) · 60 s · hotplate

Exposure dose: 262 mJ/cm² @ 365 nm

Post-exposure bake: 120 °C · 60 s

Develop: Developer AZ 726MIF · Time 60 s · Method puddle

Hardbake: 100–115 °C