

NR7-1500PY – run sheet

Futurrex, Inc.

nanyte.com/photoresists/nr7-1500py · last updated 2026-07-26

Thickness: 1.2–3 μm

Softbake: 150 °C · 60 s · hotplate

Exposure dose: 390 mJ/cm² @ 365 nm