

S1822 – run sheet

Shipley Company

nanyte.com/photoresists/s1822 · last updated 2026-07-26

Softbake: 115 °C · 60 s · hotplate

Develop: Developer MICROPOSIT MF-319 Metal-Ion-Free (MIF)
DEVELOPER family